

## IZONIL PLUS

Industrially dry-mixed 100% waterproof breathable plastering mortar with dehumidifying ability based on Portland cement and unique natural admixture (Izocomponent) and reinforced with fibers for external / internal and positive / negative application on above-ground and under-ground smooth vertical and horizontal concrete surfaces as replacement for general purpose plastering mortars, renovation plastering mortars and diffusion-closed waterproof membranes and coatings.

### DESCRIPTION

100% waterproof plastering mortar (resistant against water pressure 5 BAR / 0.5 MPa with water penetration less than 1 mm) and dehumidifying plastering mortar (with high volume of micropores which allows permanent dehumidifying process of wet substrate). Provides long-term solution to a problem of water penetration on the surface of the wall (when applied on negative side) and long-term solution to a problem of water penetration to the wall (when applied on positive side) and simultaneously provides long-term solution of ventilation and drying of wet walls (when applied both on negative and positive side). It does not contain any harmful or toxic ingredients (suitable to be used in direct contact with drinking water).

### ADVANTAGES

- ⊙ World-unique plastering mortar - simultaneously 100% waterproof, breathable and dehumidifying
- ⊙ Resistant against penetration of rain water and running water
- ⊙ Resistant against penetration of water under pressure up to 5 BAR (tested according EN 12390-8)
- ⊙ Water penetration less than 1 mm under 5 BAR water pressure during 72 hours test
- ⊙ Highly breathable (water vapor diffusion coefficient < 15)
- ⊙ Excellent adhesion to the substrate with minimum waste during application
- ⊙ Resistant against salt crystallization and sulphur-resistant
- ⊙ Applicable on damp surface
- ⊙ Applicable manually or by plastering machine
- ⊙ Applicable above-ground and underground, externally and internally, positive and negative side
- ⊙ Non-toxic, suitable to be used in direct contact with drinking water

### USAGE

Applicable on vertical surface (smooth concrete wall - precast or cast-in-place) and horizontal surface (concrete slab - floor and roof deck) both for renovation of existing / historical buildings and new buildings:

- ⊙ Basements, cellars, shafts and underground parts of buildings
- ⊙ Wall plinths or whole wall areas internally and externally
- ⊙ Roof decks, balconies, terraces
- ⊙ Bathrooms, showers, toilets to prevent water penetration between floors
- ⊙ Concrete water tanks, swimming pools, fish ponds or other concrete water-storage facilities

### TECHNICAL DATA

Appearance / color	Powder / grey
Chemical composition	Portland cement, natural admixture Izocomponent, PP fibers
Packaging	25 kg plastic woven bag
Shelf life	Minimum 18 months

Water / powder ratio	10-11 liters of clean water / 25 kg of IZONIL PLUS powder
Pot life / workability	Minimum 3 hours (at temperature 20 °C)
Thickness of layer	One layer from 4 mm to 5 mm
Coverage / consumption	At thickness 4-5 mm      1 m <sup>2</sup> = 5,5 kg of IZONIL PLUS powder 25 kg of IZONIL PLUS powder = 4,5 m <sup>2</sup>
Dry bulk density of hardened mortar	1390 kg/m <sup>3</sup> ± 50 kg/m <sup>3</sup>
Compressive strength after 28 days	≥ 34,6 N.mm <sup>-2</sup>
Adhesive strength	≥ 1,6 N.mm <sup>-2</sup>
Water penetration depth under pressure 5 BAR (0,5 MPa)	≤ 1 mm*

\* Note: Tested according EN 12390-8 (Testing hardened concrete, part 8: depth of penetration of water under pressure). Samples were exposed to water pressure 5 BAR (0,5 MPa) for 72 hours. Water pressure 5 BAR (0,5 MPa) is equivalent to pressure of water column with height 50 meters.

## SURFACE PREPARATION

IZONIL PLUS is designed to be applied on smooth concrete substrates (precast concrete wall, cast-in-place concrete wall and concrete slab).

The substrate must be solid, cement grout-free, free of dirt, oil, grease, dust, paint or other dirt and loose parts. It must not be greasy, acid, water-repellent or alcoholic base. The substrate must be thoroughly moistened immediately before applying fresh IZONIL PLUS. It is recommended to clean the substrate with a water pressure cleaner.

## MIXING

It is advisable to use a gravity mixer (concrete mixer) or hand-held electric mixer to mix IZONIL PLUS.

Water is always added first, 10 - 11 l of water per 25 kg of IZONIL PLUS. Nothing else is added into mixed composition.

Gravity mixer (concrete mixer): Add the prescribed amount of water into the mixer first, followed by IZONIL PLUS powder and mix for at least 10 minutes in constant slowly mixing, into a homogeneous smooth slurry.

Hand-held electric mixer: Add the prescribed amount of water into a suitable mixing container, followed by IZONIL PLUS powder. Mix for at least 5 minutes with constant slowly mixing into a homogeneous smooth slurry. Then let the slurry rest for 5 minutes and then mix again for 1 minute. Mixed IZONIL PLUS must be used within 3 hours.

## APPLICATION

IZONIL PLUS is applied by a plaster spraying machine or manually using plastering trowel.

IZONIL PLUS is being laid on to prepared surface in the recommended layer of 4-5 mm. Subsequently, fiberglass mesh is applied (pressed into) to the fresh layer of IZONIL PLUS and smoothed down with a trowel.

The fiberglass mesh should be as close as possible to the surface of IZONIL PLUS. We recommend roughening the surface with a sponge or plastic broom. Recommended size of fiberglass is 5 x 5 mm and weight 145 grams / m<sup>2</sup>.

## CLEANING

Clear water is used for disposal of IZONIL PLUS for the tools and equipment. Hardened material can be disposed only in a mechanical way.

## CARE AFTER APPLICATION

It is necessary to prevent the IZONIL PLUS from too fast drying since the optimal moistness enables permanent hydration of cement materials and minimization of cracking.

Protect freshly applied IZONIL PLUS prior to rapid drying using appropriate protective methods for at least 5 days, especially at dry and windy weather, or when exposed to direct sunlight.

### FINAL COATING / PAINTING

If IZONIL PLUS is applied on concrete wall and it is required to align the surface before final coating / painting, product IZONIL HARD can be used as second layer after IZONIL PLUS to align the surface. IZONIL HARD can be applied 24 hours after application of IZONIL PLUS.

Let IZONIL PLUS to dry / harden at least 3 weeks before finishing the surface. IZONIL PLUS can remain exposed without any final coating / painting. If final coating / painting is required, decorative coatings with high water vapor permeability should be used (highly breathable - diffusion-open decorative coatings / paints like silicate paints, cement paints, lime paints). If you are using a different type of paint, check its suitability with the distributor.

In case tiles are used, it is recommended to use usual tile adhesive to stick tile to the surface. Grout for tile gaps should be breathable (not silicone-based) to preserve breathability of the surface.

### IMPORTANT

When plastering extremely moist substrates with IZONIL EXTRA (e.g. basement), aggregation of water drops onto IZONIL EXTRA surface can occur. It is inherent forcing the water out of vicinity and the drops will disappear when IZONIL EXTRA cures.

Individual parameters of preparation, mixing and application of the product stated in this data sheet could vary by country, conditions and climate where the product is used. It is important to adjust parameters for specific conditions of usage. Please contact us in case of any questions regarding the usage of IZONIL PLUS (by email [vietnam@izonil.eu](mailto:vietnam@izonil.eu) or through website [www.izonil.eu](http://www.izonil.eu) where you can also find video tutorials for preparation and application).

### LIMITATIONS AND WARNINGS

- ⊙ No additives other than pure water are added to IZONIL PLUS
- ⊙ IZONIL PLUS is not applied at direct sunlight and / or strong wind or rain
- ⊙ IZONIL PLUS is only applied on a solid, pre-prepared substrate
- ⊙ The freshly applied IZONIL PLUS must be protected from rain for at least 24 hours (at 20 ° C)
- ⊙ The newly applied IZONIL PLUS must be protected from direct sunlight for at least 48 hours
- ⊙ If IZONIL PLUS is applied inside, it is necessary to ensure proper ventilation of the room for optimum drying of the wall
- ⊙ Mixed IZONIL PLUS can only be processed at air and substrate temperature above + 5 ° C
- ⊙ With the expected freeze, it is not recommended to use IZONIL PLUS
- ⊙ Potable water or water according to EN 1008: 2003 is used for mixing of IZONIL PLUS
- ⊙ Unused IZONIL PLUS remnants are mixed with water, allowed to cure and disposed as construction waste
- ⊙ Contaminated packagings are disposed as hazardous waste (see safety data sheet)

### LEGAL NOTICE

The information and, in particular, the recommendations relating to application and final use of IZONIL products are provided in good faith, resulting from the present knowledge and experience with the products when properly stored, handled and applied under normal conditions in accordance with the recommendations of RED LION COMPANY LTD. or its distributors. As long as the use and processing of the product is not subject to our direct influence, we will not be liable for any damages caused by its misuse. We reserve the right to make changes resulting from technical progress.

### FIRST AID, SAFETY AND HYGIENIC RULES

Detailed safety and health information as well as detailed precautions are provided in the IZONIL PLUS safety data sheet.

### MANUFACTURER

RED LION COMPANY LTD.

Ha Lam Industrial Zone, Binh Phuc Commune, Thang Binh District, Quang Nam Province, Vietnam

[vietnam@izonil.eu](mailto:vietnam@izonil.eu)

[www.izonil.eu](http://www.izonil.eu)